



S2161

SYNTECOL BÁZE

synthetic glossy top paint

Colour shades: According to customer's requirements - the tinting equipment of the DEKOR range TSCL (COLORLAK tinting system) enables preparing several thousand colour shades according to COLORLAK, RAL, EUROTREND, NCS and other colour charts from the basic bases and 14-16 COLORTREND DECO tinters.

Use: The SYNTECOL BÁZE S2161 paint is designed for surface treatment of wood and metal exposed to direct climatic effects (windows, doors, door cases, fences, eaves, etc.). It is also used for the renovation and maintenance of the objects previously treated with oil or synthetic coating compositions. The coatings performed while following the correct procedure have a very good resistance to weather effects.

Paint preparation prior to application: Open the packaging immediately before use and thoroughly mix the content. Any skin (which is not a flaw) should be removed carefully. Do not stir too rapidly in order to avoid mixing too much air into the paint. If needed and according to the way of application, thin up with a suitable thinner and strain, if necessary. Use up the content as soon as possible after opening the original containers. Any left-over paint should be kept in a sealing container with minimum air space above the paint level.

Application: Using a brush or spraying at a temperature between 15-25 °C and a relative air humidity up to 75 %.

Thinner: S6006 or C6500 for application using a brush, S6001 for spraying.

An example of the coating process:

*** Wood treatment for exterior use**

1. 1 layer of FUNGISTOP S1031, drying time 24 hours
2. 1 layer of SYNTECOL PRIMER S2070, drying time 24 h, resanding by 240-280 grade sanding paper
3. 1-2 layers of SYNTECOL BASE S2161 in an interval of 24 hours

*** Metal treatment for exterior use**

1. 1 layer of SYNOREX (e.g., S2000, S2003), drying time 5 hours
2. 2 layers of SYNTECOL BÁZE S2161 in an interval of 24 hours

Note: Quality of the paint system is guaranteed by its manufacturer provided that the above paints are used and the prescribed application procedures are adhered to.

Properties of the paint:

Outflow time from a cup with a nozzle of Ø 4 mm	150-250 s
Density	0.9-1.13 g/cm ³
Drying	resistant against dust for common handling
	maximum 8 hours maximum 48 hours

Properties of the dry coating: (after 3 days from the application)

Gloss, (GU)	min. 85 (gloss)
-------------	-----------------

Theoretical spreading rate: 14-15 m² from 1 litre in one layer.

Packaging: As per the current offer.

COLORLAK, a.s., Tovární 1076, 686 03 Staré Město, Czech Republic
Phone: +420 572 527 111, **Info:** +420 800 145 555, www.colorlak.cz

Shelf life: At temperatures between 5 - 25 °C for the duration of the shelf life indicated on the package of the coating material.

Disposal: Containers/unused product should be handed over to a person authorised for disposal of wastes or to a hazardous waste collection point established by the local authorities.



Product classification:

Signal word: **Warning**

H226	Flammable liquid and vapour.
H336	May cause drowsiness or dizziness.

For details, see the Safety Data Sheet of this product.

“The user is responsible for correct use of paints or for the composition and correct application of a paint system, i.e. the user must always consider all circumstances – conditions of application and processing that could affect the final quality of surface treatment.

A complaint relating to a colour shade can be acknowledged only under the condition of a previously prepared test coating on a small area, in accordance with the mandatory technological process, which accompanies the complaint. No claims filed after using up the product will be taken into consideration. COLORLAK, a.s. reserves the right to change data in technical and advertising materials without any prior notice.”

“The technical recommendations contained in this Catalogue Sheet are given based on our experience and best knowledge of the state of the art in science and practice; they are not binding and they do not constitute any obligations unless expressly defined in the purchase contract.”

Marketing, 8/2026

